

PLAY SAFE HOCKEY PE "PERFECT EVERYTIME"

PLAY SAFE
TURF & TRACK

ITHACA, NEW YORK

Manufactured By Controlled Products



PROPERTY

DESCRIPTION

Primary Yarn Polymer	Polyethylene
Yarn Cross Section	Texturized Polyethylene Monofilament
Standard Color	Verde/Olive
Additional Colors Available	White; Yellow
UV Stabilized	Yes
Fabric Construction	Tufted
Primary Backing	ArmorLoc™ 3L
Coating Type	SilverBack™ Polyurethane
Perforations	Yes
Polyethylene Yarn Denier/Ends	6000/8
Infill	N/A
Pile Height	3/8"
Pile Weight	48 oz.



APPLICATION

Installed by a company with over 100 years of combined field hockey installations. Our durability comes from the technologically advanced Silverback™ coating along with the highest performance yarn available in the market place. Play Safe Hockey PE is designed to hold up to the punishment Field Hockey dishes out. It is the ultimate wet or dry Field Hockey surface.

PLAY SAFE HOCKEY PE "PERFECT EVERYTIME"



Manufactured By Controlled Products

FINISHED FABRIC	ENGLISH SYSTEM		METRIC SYSTEM		ASTM TEST F-1551
<i>Nominal Specification</i>	<i>Value</i>	<i>Units</i>	<i>Value</i>	<i>Units</i>	<i>Method</i>
Pile Height (Nominal)	.375	In.	9.525	mm.	D-5823
Face Weight	48	oz/yd ²	1627	g/m ²	D-5828
Total Fabric Weight	77	oz/yd ²	2611	g/m ²	D-5828
Primary backing Weight	7.4	oz/yd ²	251	g/m ²	D-5828
Secondary Coating Weight	22	oz/yd ²	746	g/m ²	D-5828
Tuft Bind	>10	lbs.	>3.6	Kg.	D-1335
Grab Tear Strength (Average)	>200	lbs.	>91	Kg.	D-2256
Lead Content	<50	ppm	<50	ppm	D-2766
Total Yarn Linear Density	6,000	Denier	6,667	D-Tex	D-1577
Tensile Strength	22	lbs.	10	Kg.	D-5034
Stitch Rate	25	Per 3"	32.75	Per 10	D-5793
Machine Gauge	0.1875	In.	0.48	cm	D-5793
Flammability	TEST	PASSED	TEST	Cm.	D-2859
Water Permeability	>30	In./Hr.	>76	PASSED	F-1551
Fiber Thickness	5.9	mils	150	Cm./Hr.	D-3218
Fabric Width	15'	Ft.	4.6	microns	None

FIELD RENDERING

